

DAPRO® BEZ 75

Anti-sagging Agent

GENERAL INFORMATION

DAPRO BEZ 75 is used in non-aqueous coatings as an effective auxiliary to fight settling and sagging. It is particularly useful in aromatic-free formulations.

CHEMICAL & PHYSICAL PROPERTIES

Appearance	clear liquid
Active content	approx. 77 - 78 %
pH, 10 % solution in water (ASTM D 1172)	6.5 - 7.5
Density 20 °C (ISO 2811-2)	approx. 1040 kg/m ³
Viscosity, 25 °C (DIN 53015)	max. 1000 mPa.s
Solubility	soluble in water
Composition	surface active agent, aromatic free.

These are typical properties not to be used for specification purposes.

APPLICATIONS

DAPRO BEZ 75 can be used in most non-aqueous coatings e.g. air-dried alkyd, alkyd-melamine, acrylic, nitrocellulose, chlorinated rubber and epoxy coatings. It is suitable also for wash primers and high-solid paints. According to experience, **DAPRO BEZ 75** cannot be applied to systems containing zinc-powder.

- As anti-settling agent:
DAPRO BEZ 75 counteracts the formation of a hard, un-stirtable sediment during storage. The effectiveness of **DAPRO BEZ 75** as an anti-settling agent is shown especially in industrial primers and dipping varnishes.
- As anti-sagging agent:
DAPRO BEZ 75 improves sag resistance in dipping varnishes, spray paints and in varnishes applied by brush. **DAPRO BEZ 75** remains active even after extended storage.
- Other applications and properties:
DAPRO BEZ 75 gives a thixotropic character to coatings, even if the product is post added. Improves the brushability and if added to the pigment paste before the dispersing process, has a positive influence on the wetting and dispersing of the pigment.

- **DAPRO BEZ 75** can be applied as a swelling and wetting agent for various types of organoclay thickening agents. By using **DAPRO BEZ 75** instead of a polar activator like methanol/water, soft easily workable yet activated BENTONE pastes are obtained.
- We recommend the following composition:
 - 85 % White spirit
 - 10 % BENTONE 34 organoclay
after approx. 3 min. dispersing add:
 - 5 % **DAPRO BEZ 75**
mix for approx 7 min.
 - 100 % BENTONE 34 paste to be used after 24 hours

KEY PROPERTIES

FEATURE	CONSEQUENCE
• liquid	- easy addition, may be post-added as a - corrective agent
• imparts a thixotropic character to the paint	- reduces paint sagging after application - reduces sedimentation improves brushability
• anionic character	- aids the production of BENTONE organoclay pastes

INCORPORATION

DAPRO BEZ 75 can be added at any stage of the coating manufacture. However, when used as an anti-settling agent, we recommend the addition before the dispersing process, as this will result in better distribution of the product on the pigment.

LEVELS OF USE

In most cases good results are obtained at a concentration of 0.2 - 1.0 %, calculated on the total quantity of the paint. We recommend to determine the optimum dosage in each case individually.

HEALTH AND SAFETY

Before using this product please consult our Safety

continued...

DAPRO[®] BEZ 75

Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

SHELF LIFE

DAPRO BEZ 75 has a shelf life of 3 (three) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Jul 2018

North America

Elementis Specialties, Inc.
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563