

## RHEOLATE® 185

### Low to Mid-Shear Acrylic Thickener to Replace Cellulosic Thickener

#### GENERAL INFORMATION

**RHEOLATE 185** rheological additive is a cost effective alkali soluble associative thickener that was specially designed to replace cellulosic thickeners. It can be used in water based coatings either as a primary or as a co-thickener. It offers better applied hide, less spattering, resistance to mud-cracking in thick coatings typically seen in high build coatings while maintaining the in-can feel of paint based on cellulosic thickener.

**RHEOLATE 185** is supplied as low viscosity liquid it provides ease of addition and incorporation in paint. It's resistance to microbial spoilage enhances long term paint stability without loss in viscosity as seen in cellulosic based paint.

#### CHEMICAL & PHYSICAL PROPERTIES

Composition	acrylic emulsion in water
Appearance	milky white liquid
Active Content	30 %
Specific Gravity	ca. 1.05
Brookfield Viscosity cps	<20 mPa.s (Brookfield LV, Spindle#1, 100RPM, 25°C)
Solvent	water
pH Value	2 - 3.5
Storage Precautions	protect from freezing

These are typical properties not to be used for specification purposes.

#### APPLICATIONS

- Waterborne finishes based on different latex systems.
- Adhesives and sealants
- Tile grouts
- Plasters

#### KEY PROPERTIES

- Provides low to mid-shear viscosity
- Shear thinning
- Provides excellent leveling
- Improves applied hide
- Cost effective alternative to cellulosic thickener
- Solvent and APEO free
- Low viscosity makes it easy to incorporate
- Spatter resistance
- Mud crack resistance in thick films
- Retains viscosity even after paint dilution
- Prevents hard settling upon dilution
- Stable viscosity over time
- Resists microbial spoilage

#### INCORPORATION

**RHEOLATE 185** can be used alone or together with other rheological additives to achieve ideal performance properties.

**RHEOLATE 185** is an alkali swellable thickener and requires proper pH adjustment with an alkali (like ammonium hydroxide or amino methyl propanol) for complete activation. In a typical latex paint, a pH of 9.0 - 9.5 is usually recommended.

The addition can be made at any point in the process, but is normally made in the let-down or towards the end of the formulation process. At this stage **RHEOLATE 185** can be added slowly to the formulation under good mixing conditions without dilution. Under slow speed mixing conditions, dilution with water is recommended to ensure efficient activation of the additive and to avoid latex shock. (**RHEOLATE 185**: water ratio 1:1 to 1:5 by weight).

#### LEVELS OF USE

Typical use levels of **RHEOLATE 185** are 0.5 % to 2 % as delivered on total system weight.

Please run a ladder test to determine the most suitable dosage before use.

*continued...*

## RHEOLATE® 185

### STORAGE RECOMMENDATIONS

**RHEOLATE 185** should be kept above 4 °C (40 °F). In the event of accidental freezing, thaw gently, spread a portion between glass slides and examine for granules. If found, do not use.

### HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

### SHELF LIFE

**RHEOLATE 185** has a shelf life of 2 (two) years from date of manufacture.

### QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Aug. 2018

#### North America

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563