

Adherent PPB

Adhesion Promoter

GENERAL INFORMATION

Adherent PPB is an additive which improves adhesion to non-treated polypropylene or PP / EPDM plastics.

CHEMICAL & PHYSICAL PROPERTIES

Composition	chlorinated PP
Appearance	slight yellow liquid
Non-volatile content	14 - 16 %
Solvent	toluene
Specific gravity	ca. 0.895

These are typical properties not to be used for specification purposes.

APPLICATIONS

- PP substrate primers

KEY PROPERTIES

- It is well-known that surface of PP is very difficult to adhere. Though PP can be surface pretreated with flame or corona, these treatments are limited due to their high cost of equipments or complicated operations.
- These difficulties can be overcome by simply using Adherent PPB as primer or incorporating **Adherent PPB** into paint to promote adhesion to PP, PP/EPDM substrates. The water, gasoline and heat resistance of dried film are also improved.

INCORPORATION

Primer

Dilute **Adherent PPB** with of solvent (toluene or xylene) to 5 - 10 times.

Clean the substrate to remove residual grease or release agent.

Spray the **Adherent PPB** solution, dried film thickness of 5 - 10 μm , setting for 5 - 10 minutes.

Apply acrylic lacquer or two-component PU top coat, setting for 5 - 10 minutes.

Force dry at 80 °C for 30 - 60 minutes.

As additive in paint

Add 10 - 15 % of **Adherent PPB** based on total formulation and mix thoroughly.

Clean the substrate to remove residual grease or release agent.

Apply the paint containing **Adherent PPB**, setting for 20 - 30 minutes.

Force dry at 80 °C for 30 - 60 minutes.

LEVELS OF USE

Using as primer or 10 - 15 % based on resin.

HEALTH AND SAFETY

After storage for a long time, due to possible solvent evaporation the viscosity of **Adherent PPB** maybe will increase or become gel-like.

Under such situation, please adding toluene and heating by water bath to recover and use then with in short time.

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

Below 5 °C, appearance may be cloudy or separation, please heat(water bath) to clear than stir to uniform.

continued...

Adherent PPB

SHELF LIFE

Adherent PPB has a shelf life of 12 months from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Feb. 2018

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563