FORMULATION SHEET

ELEMENTIS

Eye Correcting Concealer

C-2060-02

DESCRIPTION

Based on WGSN x Coloro S/S 27 Key Colours, Clay. This high coverage pinkish peach colour corrector evenly corrects discoloration under the eyes. Apply before your normal tone concealer for a brightened look.

Phase	Ingredient	Supplier	%w/w
A	C12-15 Alkyl Benzoate		10.00
	C15-19 Isoalkane (Shell Silk Alkane G3)	Shell	2.00
	Caprylic/Capric Triglyceride (Palmester 3595)	KLK Oleo	0.50
	Prunus Persica Kernel Oil		0.50
	Lauryl/Isooctyl/Octyldodecyl/Dipropylene Glycol Citrate Crosspolymer (NATURALUXE™ MFF)	Elementis	10.00
	Tocopheryl Acetate		0.50
	Tocopherol (and) Helianthus Annuus (Sunflower) Seed Oil (Dermofeel® Toco 70 non-GMO)	Evonik	0.50
	Iron Oxides (CI 77492) (and) Stearoyl Glutamic Acid (and) Polyhydroxystearic Acid (BWYO-ASGP3)	Kobo Products	2.00
	Iron Oxides (CI 77499) (and) Stearoyl Glutamic Acid (and) Polyhydroxystearic Acid (BWBO-ASGP3)	Kobo Products	0.12
	Iron Oxides (CI 77491) (and) Stearoyl Glutamic Acid (and) Polyhydroxystearic Acid (BWRO-ASGP3)	Kobo Products	1.67
	CI 77891 (Titanium Dioxide) (and) Stearoyl Glutamic Acid (and) Polyhydroxystearic Acid (BTD-ASGP3)	Kobo Products	21.21
	Polyglyceryl-6 Polyhydroxystearate (and) Polyglyceryl-6 Polyricinoleate (and) Polyglycerin-6 (Emulium® Illustro)	Gattefossé	4.00
	Mica (KoboMica S-25)	Kobo Products	1.00
	Silica		1.00
B	Rhus Verniciflua Peel Cera (KahlWax 6290 Berry)	Kahl	3.00
	Cera Microcristallina (KahlWax 6202 Micro)	Kahl	2.00
	Glyceryl Behenate (Compritol® 888 CG MB Pellets)	Gattefossé	0.50
C	Deionized Water (Aqua)		32.50
	Glycerin		2.00
	Magnesium Sulfate		2.00
	Phenoxyethanol (and) Ethylhexylglycerin (euxyl™ PE 9010)	Ashland	1.00
D	Oryza Sativa Starch (Reisita Natural 9094)	Agrana	2.00

continued...

FORMULATION SHEET

ELEMENTIS

Eye Correcting Concealer

C-2060-02

PROCEDURE

1. Combine phase A and homogenize until uniform.
2. Add phase B to phase A. Heat to 85ºC with stirring until wax is melted and mixture is homogeneous.
3. Combine phase C with stirring until uniform. Heat to 85ºC.
4. Add phase C to phase A/B slowly with propeller mixing.
5. Homogenize for approximately 2 minutes.
6. Add phase D and mix until uniform.
7. Cool down to room temperature under moderate stirring.

SPECIFICATIONS

Viscosity: LVDV-I. Spindle 64. 1 rpm 370,000 –400,000 cP

Appearance: Pink thick cream

ADVANTAGES

NATURALUXE™ MFF forms a smooth, flexible film that improves coverage uniformity, boosts wear resistance, and helps the formula stay comfortably in place on delicate undereye skin.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2023, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Registered trademark of Elementis Specialties, Inc.

North America
Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
T: +1 609 443 2500

Europe
Elementis PLC
The Bindery 5th Floor
51—53 Hatton Garden
London EC1N 8HN, UK
T: +44 207 067 2999

Asia
Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
T: +86 21 5774 0348