

Hypomer MT-2550K

Functional Matting Resin

GENERAL INFORMATION

Hypomer MT-2550K is a hydroxyl acrylic resin that gives excellent matting effect yet better clarity and transparency than conventional 2K PU coatings formulated with matting agents e.g. silica.

Hypomer MT-2550K is based on special chemical reaction process to generate crosslink particle during the reaction and provide matting effect and other benefits better than silica based matting coatings.

CHEMICAL & PHYSICAL PROPERTIES

Composition	hydroxyl acrylic copolymer
Appearance	white to milky viscous liquid
Non-volatile content	48.5 - 52.0 %
Solvent	n-Butyl acetate/propylene glycol monomethyl ether acetate/methylcyclohexane
Specific gravity	ca. 1.02
Dynamic viscosity	2000 - 12000 cP (25 °C)
Acid value	15.0 - 40.0 mg KOH/g (100 %)
OH value	ca. 41.3 mg KOH/g (as received)
OH %	ca. 1.25 % (as received)
Tg	ca. 66 °C (measured by DSC)

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Plastic coatings
- Industrial coatings
- Wood coatings
- Transportations
- Inks

KEY PROPERTIES

- Excellent matting function
- Good scratch resistance
- Good weather resistance
- Good touch feel
- Environmentally friendly solvent composition
- Easy incorporation
- Homogenous gloss level over a wide range of dry film thickness leads to a wider application window

SOLUBILITY

	Dilution
Mineral spirit (B.P. 100 - 140 °C)	-
Toluene	+
Xylene	+
Ethyl acetate	+
n-Butyl acetate	+
Methyl ethyl ketone	+
Propylene glycol monomethyl ether acetate	+
+= soluble	
O= limited soluble	
- = insoluble	

COMPATIBILITY

	Resin Solution	Dried Film
Hypomer FX-2050	+	+
Hypomer FX-2052	+	+
Hypomer FX-2060AF	+	+
Hypomer FX-2451F	+	+
+= compatible		
O= limited compatible		
- = incompatible		

INCORPORATION

Due to its thixotropy, viscosity increase upon storage is possible. In order to get the best performance, please stir well before use.

Basically, **Hypomer MT-2550K** is compatible with most of low hydroxyl value acrylic resins. Gloss adjustment is achievable by mixing **Hypomer MT-2550K** with other acrylic resins. Mixing ratio should be determined experimentally.

Sedimentation may occur after diluting to lower viscosity. Formulate with anti-settling agent is recommended.

continued...

Hypomer MT-2550K

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

SHELF LIFE

Hypomer MT-2550K has a shelf life of 12 months from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V02 Mar. 2019

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563