

# Hypomer FS-2460A

## Acrylic Polyol Resin

### FEATURES

- Low hydroxyl content
- Fast drying and curing speed
- Good adhesion to plastic substrates
- Good weather resistance
- Good pigment wetting

### CHEMICAL & PHYSICAL PROPERTIES

Composition	hydroxyl acrylic copolymer
Appearance	clear viscous liquid
Color value	≤100 APHA
Non-volatile content	59 - 62 %
Solvent	toluene / methyl isobutyl ketone
Specific gravity	ca. 1.01
Acid value	11.5 - 14.0 mg KOH / g (100%)
OH value	ca. 47.52 mg KOH / g (as received)
OH %	ca. 1.44 % (as received)
Tg	ca. 60 °C (measured by DSC)

These are typical properties not to be used for specification purposes.

### APPLICATIONS

- Plastic coatings
- Automobile, motorcycle base coat and pigmented coatings
- Transportation and industrial application

### SOLUBILITY

	Dilution
Mineral spirit (B.P. 100 - 140 °C)	O
Toluene	+
Xylene	+
Ethyl acetate	+
n-Butyl acetate	+
Methyl ethyl ketone	+
Propylene glycol monomethyl ether acetate	+

### COMPATIBILITY

	Resin Solution	Dried Film
Hypomer FS-2050	+	+
Hypomer FS-2060	+	+
Hypomer FS-2060B	+	+
Hypomer FS-2820	+	+
Hypomer FS-2860A	+	+
Hypomer FS-3060	+	+
Hypomer FS-3075	+	+
Hypomer FS-4365	+	+
Hypomer FS-4660	+	+

+ = soluble / compatible

O = limited soluble / compatible

— = insoluble / incompatible

Mixing ratio of **Hypomer FS-2460A** with resin is 1/1.

### HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

### STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

*continued...*

## Hypomer FS-2460A

### SHELF LIFE

**Hypomer FS-2460A** has a shelf life of 2 (two) years from date of manufacture.

### QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2021, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*© Trademark of Elementis Specialties, Inc.*

V01 Jan. 2021

#### North America

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563