

## M-P-A<sup>®</sup> 40X

### Rheological Additive

#### GENERAL INFORMATION

**M-P-A 40X** a translucent paste thixotropic rheological additive for solvent based coatings. It prevents pigment settling and gives good suspension performance. It is especially excellent for industrial, traffic and marine paints.

#### CHEMICAL & PHYSICAL PROPERTIES

Composition	complex polyolefin compound and xylene
Appearance	translucent yellow soft liquid.
Non-volatile content	39 - 41 %
Solvent	xylene
Specific gravity	ca. 0.88 (20 °C)
Solubility	soluble in aliphatic and aromatic hydrocarbon solvent when heated.
Flush point	ca. 30 °C

These are typical properties not to be used for specification purposes.

#### APPLICATIONS

- Especially designed for industrial, traffic and marine paints
- Chlorinated rubber paints
- Zinc rich primer
- Red lead paints
- Epoxy paints
- Oil and oil modified alkyd resin paints

#### KEY PROPERTIES

- **M-P-A 40X** is used in almost all solvent based coatings
- The main function is the prevention of hard settling (viscosity increase type)
- Works as an anti-silking agent
- Does not exhibit any trouble such as viscosity increase and seeding

- Prevents pigment agglomeration, settling and hard caking
- Easily dispersible and rapidly dispersed than other conventional anti-settling agents
- It maintains excellent viscosity stability in storage

#### INCORPORATION

**M-P-A 40X** should be added to the mill base stage.

Can be carried out 30 - 50 °C. No special care for the temperature adjustment to take effect.

For maximum efficiency in industrial coating, the temperature should exceed 45 °C.

Sand mill, ball mill, three roll mill etc. are proper dispersing equipment.

#### LEVEL OF USE

The optimum levels usage will vary depending on the system, the type of pigmentation and the degree of anti-settling protection required.

Industrial coatings : 0.5 - 1.0 %

The other paints : 0.2 - 0.5 % (by weight)

#### HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

Should be stored in cool dry place.

Keep container tightly closed after used.

Stored away from direct sunlight and other sources of heat.

*continued...*

## M-P-A<sup>®</sup> 40X

### SHELF LIFE

**M-P-A 40X** has a shelf life of 12 months from date of manufacture.

### QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*© Trademark of Elementis Specialties, Inc.*

V01 Jan. 2019

#### North America

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563