

BENTONE GEL[®] 2

Rheological Additive for Solvent-based Coatings

GENERAL INFORMATION

BENTONE GEL 2 is a predispersed BENTONE 38 gel rheological additive for industrial solvent-based systems. It is more effective than a simple BENTONE pregel, as **BENTONE GEL 2** provides immediate full thixotropic effect with no after-bodying or viscosity drift on aging.

CHEMICAL & PHYSICAL PROPERTIES

Composition	BENTONE 38 in a blend of n-butanol and xylene
Color/ Form	Biege / Very soft gel
Total Solids	17.5%
Density	0.92 g/cm ³
Flash Point	78 °F / 26 °C

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Aromatic solvent-based systems
- Stains and varnishes
- Blended (including aromatics) solvent-based systems
- Industrial/Maintenance paint systems
- Light industrial finishes

KEY PROPERTIES

- Improved pigment suspension
- Improved sag resistance
- Reduced penetration
- Reduced flooding and floating

INCORPORATION

BENTONE GEL 2 may be added to the initial mill base or, preferably, shortly before the let down. When used as a corrective agent in a completed batch, reduce the **BENTONE GEL 2** first with an equal volume of paint added in several small increments under agitation. When the mixture is smooth and fluid, pour it into the batch and stir for 10 to 15 minutes.

LEVELS OF USE

In a typical coating, 10-20 lbs of **BENTONE GEL 2** generally takes the place of 2 to 3 lbs of dry BENTONE 38. The optimum concentration may be higher depending on the individual system and its requirements.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep containers in a cool, dry location. Partially used containers should be tightly resealed for storage.

SHELF LIFE

BENTONE GEL 2 has a shelf life of 4 (four) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

BENTONE GEL[®] 2

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Apr. 2018

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563