

## Disponer 904S

### Wetting and Dispersing Agent

#### GENERAL INFORMATION

Additive for polar and non-polar systems. Activity for the most part independent of the binder. For systems based on alkyd, epoxy, epoxies, acrylic resins, PUR, polyesters and vinyl compounds.

#### CHEMICAL & PHYSICAL PROPERTIES

Composition	solution of polycarboxylic acid polymer with modified polysiloxane
Appearance	yellow to brown, clear liquid
Non-volatile content	49 - 51%
Solvent	xylene / diisobutyl ketone
Specific gravity	0.92 - 0.95
Acid value	180 - 220 mg KOH / g
Refractive index	1.471 - 1.481 (25 °C)

These are typical properties not to be used for specification purposes.

#### APPLICATIONS

- Ready paints
- Epoxy paints
- Polyester / melamine
- Acrylic / melamine
- Alkyd / melamine
- 2K polyurethane
- Gravure printing inks / screen printing inks

#### KEY PROPERTIES

- Among its other properties, **Disponer 904S** is highly effective in preventing floating of titanium dioxide pigments in paint formulate- ions also containing colored pigments. As a pigment dispersing and wetting agent, it generally prevents hard settling deposits when basic pigments and carbonate fillers are used.
- In contrast to certain silicone oils, **Disponer 904S** does not as a rule produce cratering. It is a very effective flow promoter and eliminates surface disturbances in the film when added at the proper level. In addition, the scratch resistance and slip properties of the film are considerably improved **Disponer 904S** can be used in both water-thinnable and solvent-containing systems.

- **Disponer 904S** functions independent of the binder system to a very great degree, allowing a wide range of use.

#### INCORPORATION

Incorporated before grinding, dispersing with pigment.

**Disponer 904S** can also be used as a post-additive, and is useful for corrections at this point. In this case, the amount to be used is 0.1% to 1.5 %, based on the total formulation.

Please check the optimum dosage and test compatibility before use.

#### LEVELS OF USE

Organic pigments : 2.0 - 5.0 % based on pigment.

Inorganic pigments : 0.5 - 3.0 % based on pigment.

#### HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

Below 5°C, or above 40°C appearance may be cloudy or separation, when below 5°C, please heat water bath to clear then stir to uniform, but above 40°C, please return to 10 - 30 °C then stir to uniform.

It sensitive to moisture and should therefore be stored in its sealed original containers.

*continued...*

## Disponer 904S

### SHELF LIFE

**Disponer 904S** has a shelf life of 2(two) years from date of manufacture.

### QUALITY ASSURANCE

Quality system at the site manufacturing this product complies with and is certified to ISO 9001 quality standards.

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

© Copyright 2022, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Jul. 2022

#### North America

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563