

BENTONE® EW HV

Rheological Additive for Waterborne Systems

GENERAL INFORMATION

BENTONE EW HV additive is a highly beneficiated, easily dispersible powdered smectite clay.

CHEMICAL & PHYSICAL PROPERTIES

Composition	Highly beneficiated smectite clay
Color / Form	Milky-white, soft powder
Apparent (bulk) density	Approx. 0.4 g/cm ³
Particle Size	min 94% thru 200 mesh
Viscosity(21 °C)	2200-2600 mPa·s

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Adhesives
- Ceramic compounds
- Ceramic glazes
- Corrosion-inhibitive primers
- Cosmetics
- Crop protection agents
- Electrodeposition coatings
- Latex paints
- Foundry paints/foundry resins (washes)
- Oil-in-water emulsions
- Other water-borne paint systems
- Paper coatings
- Polishes and cleaners
- Welding electrodes

KEY PROPERTIES

Rheological properties

- provides thermostable aqueous phase viscosity control
- imparts thixotropy

Application performance

- enhances texturing and stippling effects
- improves workability/application of plasters
- no throwing power loss in electrostatic systems
- promotes fast water release

System stability

- compatible with synthetic resin dispersions
- electrolyte emulsions
- stabilises emulsions
- provides good stability in electrostatic coating baths
- prevents hard settlement of pigments/fillers
- reduces syneresis
- minimises floating/flooding of pigments

Easy to use

- can be incorporated as powder or as an aqueous 3 - 4 wt % (solids) pregel.

INCORPORATION

BENTONE EW HV additive is easy to process. No increased temperature is required.

1. Add **BENTONE EW HV** to a vessel containing only water, pH 7.0 - 8.0. If necessary, adjust pH level. pH can be adjusted with appropriate alkali but triethanolamine can cause degelling. High or low pH during dispersion can lead to inhomogeneous gel formations and reduced efficiency.
2. Mix at highest practicable speed for 10 minutes.
3. After sufficient hydration time, introduce glycols, defoamers, biocides, dispersants etc. (mix)
4. Add pigments, fillers, and active ingredients and disperse.
5. Complete dilution.

BENTONE EW HV additive is stable within the range pH 6 - 11.

LEVELS OF USE

Typical addition levels are 0.1-1.0 % **BENTONE EW HV** additive by weight of total formulation, depending upon the degree of suspension, the rheological properties or viscosity required.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

continued...

BENTONE® EW HV

STORAGE RECOMMENDATIONS

Store in a dry place. **BENTONE EW HV** additive will absorb moisture in high humidity conditions.

SHELF LIFE

BENTONE EW HV has a shelf life of 4 (four) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 July 2018

North America

Elementis Specialties, Inc.
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563