

Hypomer AC-7450

Thermoplastic Acrylic Resin

FEATURES

Fast drying
High gloss and good hardness
Good alcohol resistance

CHEMICAL & PHYSICAL PROPERTIES

Composition	acrylic copolymer
Appearance	clear liquid
Color value	≤50 APHA
Non-volatile content	48 - 52 %
Solvent	toluene
Specific gravity	ca. 0.98
Dynamic viscosity	1300 - 2100 cP (25 °C)
Acid value	≤5 mg KOH / g (100 %)
Tg	ca. 100 °C (measured by DSC)

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Plastic coatings
- Metallic coatings
- Wood coatings

SOLUBILITY

	Dilution
Mineral spirit (B.P. 100 - 140 °C)	O
Toluene	+
Xylene	+
Ethyl acetate	+
n-Butyl acetate	+
Methyl ethyl ketone	+
Propylene glycol monomethyl ether acetate	+

COMPATIBILITY

	Resin Solution	Dried Film
Hypomer AC-7416	+	+
Hypomer AC-7435	+	+
Hypomer FX-2050	+	+
Hypomer FX-2060A	+	+
Hypomer FX-2460A	+	+

+ = soluble / compatible

O = limited soluble / compatible

— = insoluble / incompatible

Mixing ratio of **Hypomer AC-7450** with resin is 1/1.

HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

SHELF LIFE

Hypomer AC-7450 has a shelf life of 2 (two) years from date of manufacture.

QUALITY ASSURANCE

Quality system at the site manufacturing this product complies with and is certified to ISO 9001 quality standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2026, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

V02 Aug. 2026

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500

Europe

Elementis Portugal Lda.,
Rua Santos Pousada, no.262,
4000-478, Porto
Portugal
Tel: +351 221 215 791

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348