

## PLUSTALC H35

### Functional Extender

#### GENERAL INFORMATION

**PLUSTALC H35** is a hydrated magnesium silicate with chemical formula of  $\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2$ .

**Plustalc grades** are have a low iron content. Plustalc is suitable for such applications where a higher brightness is required.

#### APPLICATIONS

- Plastics: For automotive cabin and under the hood, appliances, pipes, powdering and profiles.

#### KEY PROPERTIES

- Pure, lamellar and very white talc with medium fine particle size, very hydrophobic, inert and soft.

#### INCORPORATION

**PLUSTALC H35** can be used as a functional extender to achieve following results:  
Consistent color, low abrasion and longer tool life.

#### LEVELS OF USE

Typical use levels for talc in plastics depending upon the application. Please contact your local sales representative for advice.

#### HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

Store dry.

#### SHELF LIFE


**PLUSTALC H35** has a shelf life of 5 (five) years from the date of manufacture.

#### QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 certificates, which guarantees that all operations are conducted according to the stipulated standards.

*continued...*

## PLUSTALC H35

|                            |  |                      |                |                   |
|----------------------------|--|----------------------|----------------|-------------------|
| <b>MINERALOGY</b>          | Talc (Mg-Silicate)   |                      | 96             | %                 |
|                            | Traces of magnesite, dolomite and chlorite   |                      |                |                   |
|                            | CAS-No. 14807-96-6   | EINECS-No. 238-877-9 |                |                   |
| <b>CHEMICAL PROPERTIES</b> | MgO  | XRF                  | 31.5           | %                 |
|                            | SiO <sub>2</sub>   | XRF                  | 60             | %                 |
|                            | Al <sub>2</sub> O <sub>3</sub>   | XRF                  | 0.6            | %                 |
|                            | Fe <sub>2</sub> O <sub>3</sub>   | XRF                  | 0.5            | %                 |
|                            | Fe acid soluble  | 1mol/L HCl, 100°C    | Not detectable | %                 |
|                            | Loss on ignition   | DIN 51081/1000°C     | 7.5            | %                 |
|                            | pH value   | ISO 787/9            | 9              |                   |
| <b>OPTICAL PROPERTIES</b>  | Whiteness Ry   | DIN 53163            | 90.5           | %                 |
|                            | CIE L*, a*, b*   | DIN 6174             | 96.5/0.0/1.3   |                   |
|                            | Yellowness index   | DIN 6167             | 2.5            |                   |
| <b>PHYSICAL PROPERTIES</b> | Top cut D98  | Sedigraph, ISO 13317 | 27             | µm                |
|                            | Median particle size D50   | Sedigraph, ISO 13317 | 10             | µm                |
|                            | Sieve residue  | ISO 787/7, 75 µm     | 0.1            | %                 |
|                            | Specific surface area  | BET, ISO 4652        | 6              | m <sup>2</sup> /g |
|                            | Oil absorption   | ISO 787/5            | 32             | g/100g            |
|                            | Hardness   | Mohs                 | 1              |                   |
|                            | Tapped density   | ISO 787/11           | 0.70           | g/cm <sup>3</sup> |
|                            | Bulk density   | DIN 53468            | 0.45           | g/cm <sup>3</sup> |
|                            | Moisture   | ISO 787/2            | 0.2            | %                 |
|                            |  |                      |                |                   |

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Minerals B.V.

V02 Dec. 2019

**North America**

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

**Europe**

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

Elementis Minerals B.V.  
Kajuitweg 8  
NL-1041 AR Amsterdam  
The Netherlands  
Tel.: +31 20 4487 448

**Asia**

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563